

TECHNICAL DATA SHEET
VAC-PAK[®] A6200/A6200M & A6000
RELEASE FILM

VAC-PAK[®] A6200/A6200M & A6000

Release film

suter-kunststoffe ag
swiss-composite.ch

Ideally suited to aerospace applications

Features and Benefits

- High temperature, tough fluoropolymer release films with excellent release characteristics combined with high elongation.
- Suitable for use with all commonly used resin systems.
- Available perforated or non-perforated
- Most commonly used in aerospace applications and has numerous OEM approvals.
- Clear blue or red for ease of identification on the cured laminate.
- Vac-Pak[®] A6200M has a one-sided textured finish to meet matte surface finish requirements

PROPERTIES

Maximum use temperature	232°C	450°F
Color	Clear blue and red	
Film	ETFE	
Standard perforation patterns	Contact us for full details	
Tensile strength (at break)	40/70MPa	6000/10000psi
Elongation (at break)	350%	
Yield	10.2m ² /kg	110 ft ² /lb/mil

AVAILABILITY

Thicknesses	12, 15, 20 and 25µm	0.0005, 0.0006, 0.001 and 0.002in
Standard length	Available on request	

STORAGE

Store in original packaging

HEALTH & SAFETY

Please refer to the product MSDS for safe handling, personal protective equipment recommendations and disposal considerations.

DISCLAIMER: The data and information provided in this document have been obtained from carefully controlled samples and are considered to be representative of the product described. Solvay does not express or imply any guarantee or warranty of any kind including, but not limited to, the accuracy, the completeness or the relevance of the data and information set out herein. Because the properties of this product can be significantly affected by the fabrication and testing techniques employed, and since Solvay does not control the conditions under which its products are tested and used, Solvay cannot guarantee the properties provided will be obtained with other processes and equipment. No guarantee or warranty is provided if the product is adapted for a specific use or purpose. Solvay declines any liability with respect to the use made by any third party of the data and information contained herein. Solvay has the right to change any data or information when deemed appropriate. All trademarks are the property of their respective owners. ©2017, Solvay. All rights reserved.

Solvay

Composite Materials HQ
4500 McGinnis Ferry Rd
Alpharetta, GA 30005-3914 USA

20 October 2017

