

SR **GreenCast 160** / SD 7160 Clear Casting Resin System



SR GreenCast 160 is an epoxy system with enhanced UV resistance, designed for casting of decorative objects, bottle prototypes, jewellery, river tables...

- Very low reactivity allowing high thicknesses up to 10 cm at 20 °C.
- High clarity polymer, colourless and with good brightness.
- Room temperature curing

		SD 7160
Reactivity level		Slow
Initial viscosity (mPa.s)	@ 20 °C	360
	@ 30 °C	250
Pot Life (500 g)	@ 20 °C	01 h 00
	@ 30 °C	40 min
Mixing ratio	By weight	100 / 42
	By volume	100 / 50
Density		1,1307
TG1 max onset	°C	61

SR GreenCast 160 resin is out coming from the latest innovations in bio-based chemistry. **SR GreenCast 160** resin is produced with a high content of carbon from plant origin. The bio-based Carbon content of our system is certified by an independent laboratory using Carbon 14 measurements (ASTM D6866 or XP CEN/TS 16640)


This is a significant technological advance on the following points:
Clarity, color, performance and guaranty of available industrial tonnages.

SR GreenCast 160 is an epoxy resin which has 37% of its molecular structure coming from plant origin.

This percentage is function of the carbon origin contained in the epoxy molecule.
The final rate of the mix bio-based carbon content will depend on the hardener choice.

SR GreenCast 160 is an epoxy system with enhanced UV resistance, designed for production by casting of decorative objects, bottle prototypes, jewellery, river tables...

- Very low reactivity allowing high thicknesses up to 10 cm at 20 °C.
- High clarity polymer, colourless and with good brightness.
- Room temperature curing
- Almost odourless.
- 2:1 ratio and very easy mixing.
- Excellent degassing.
- Excellent impact and thermal shock resistance.
- Good UV resistance



Epoxy resin SR GreenCast 160

Appearance		liquid
Color		colourless
Gardner color		≤ 0
Pt/Co Color Index		≤ 15
Viscosity (mPa.s)	@ 15 °C	2400 ± 480
	@ 20 °C	1300 ± 260
	@ 25 °C	780 ± 160
	@ 30 °C	480 ± 100
	@ 40 °C	210 ± 42
Density	@ 20 °C	1,1700
Refractive index	@ 25 °C	1,5499 ± ,002
Bio-based Carbon content (%)		37
Storage (months)	@ Ta	24

Hardener(s)


		SD 7160
Appearance		liquid
Color		colourless
Gardner color		≤ 1
Pt/Co Color Index		≤ 50
Reactivity level		Slow
Viscosity (mPa.s)	@ 15 °C	180 ± 30
	@ 20 °C	125 ± 20
	@ 25 °C	90 ± 15
	@ 30 °C	70 ± 10
Density	@ 20 °C	0,9700
Refractive index	@ 25 °C	1,459 ± ,002
Storage (months)	@ Ta	24

Mixe(s) SR GreenCast 160 / SD 7160

		SD 7160
Appearance		liquid
Color		colourless
Mixing ratio		
	By weight	100 / 42
	By volume	100 / 50
Density	@ 20 °C	1,1307
Initial viscosity (mPa.s)	@ 20 °C	360
PP 50 mm / 10 s ⁻¹	@ 30 °C	250


Reactivity for 500 g

	20 °C	30 °C	°C
Exothermic temperature (°C)	23,5	38	
Exothermic peak time	21 h 30	12 h 00	-
Time to reach 50 °C	-	-	-



Reactivity on a 6 mm thick cast

@ 20 & 30 °C



Mechanical properties on cast resin :

		SR GreenCast 160 / SD 7160		
Curing cycles		7 days @ TA	48 h @ TA + 24 h @ 40 °C	48 h @ TA + 16 h @ 60 °C
Tensile				
Modulus	N/mm ²	620	1 500	2 150
Maximum strength	N/mm ²	11,5	26	38
Breaking Strength	N/mm ²			
Elongation at max strength	%	5,9	3,3	3,1
Elongation at break	%	50	27,8	19
Flexion				
Modulus	N/mm ²	780	1 200	1 940
Maximum strength	N/mm ²	20	32	59
Breaking Strength	N/mm ²			
Elongation at max strength	%	6,2	5,5	4,9
Elongation at break	%	15	15	15
Shear				
Breaking Strength	N/mm ²	17,5	25	30
Compression				
Modulus	N/mm ²			
Yield strength	N/mm ²	30	25	65
Offset compression yield	%	12,1	10,8	10,7
Charpy impact strength				
Resilience	kJ/m ²	84	67	58
DSC glass transition				
TG1 onset	°C	45	50	58
TG1 max onset	°C			61

Tests carried out on samples of pure cast resin, without prior degassing, between steel plates.

Measures undertaken according to the following norms:

Mechanical tests:

Tension:	NF EN ISO 527-2:2012
Flexion:	NF EN ISO 178:2011
Compression:	NF EN ISO 604:2004 or NF EN ISO 844:2014 (foam product)
Charpy impact strength:	NF EN ISO 179-1:2010
Shear Strength:	ASTM D732-17 (Punch Tool)
Interlaminar shrinkage strength:	ASTM D5528-13
Toughness (GIC et KIC) :	ISO 13586:2000

Water absorption: Internal. Polymerization according to cycle, machining, weighing, time spent in distilled water at 70 °C / 48 hours, weighing 1 hour after emerging,

Thermal tests:

Glass transition DSC:	NF EN ISO 11357-2:2014 -5°C to 180 °C under nitrogen gas
T_{G1} or Onset:	1 st scan at 20 °C/min
T_{G1} maximum or Onset:	2nd scan at 20 °C/min

Glass transition DTMA:	Temperature ramp 0 °C to 180 °C @ 2°C/min under normal atmosphere
	NF EN ISO 11357-1:2016 T_G onset G'
	ASTM D4065-12 T_G peak G''

Physical tests:

Gardner color:	NF EN ISO 4630:2016	Visual method
Refractive index:	NF ISO 280:1999	
Viscosity:	NF EN ISO 3219:1994	Rheometer 50 mm, shear 10 s ⁻¹
Density on liquids:	ISO 2811-1:2016	Pycnometer
Density on solid:	NF EN ISO 1183-3:1999	Helium Pycnometer
Density on foam:	NF EN ISO 845:2009	
Gel time:	Cross G' G''	Rheometer CP50 - Shear rate 10 s ⁻¹
Green Carbone content:	ASTM D6866-16 or XP CEN/TS 16640 Avril 2014	

TA: Ambient temperature (20 to 25 °C)

LEGAL NOTES:

Information given in writing or verbally, in the context of our technical assistance and our trials, does not engage our responsibility. Information is given in good faith based on SICOMIN's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with SICOMIN's recommendations. We advise users of SICOMIN products to check by some practical trials that they are suitable for the intended processes and applications. The customer's storage, the use, the implementation and the transformation of the supplied products are not under SICOMIN's control and entirely under the sole responsibility of the user.

SICOMIN reserves the right to change the properties of its products. All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data and tolerance may vary due to circumstances beyond our control.

If our responsibility should nevertheless be involved, it would be, for all the damages, limited to the value of the goods supplied by us and processed by the customer. We guaranty the non-reproachable quality of our products, in the general context of sales and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.