

# TECHNICAL DATASHEET



**Article:** Style 220  
**Setting [threads/cm]:** 8,7/8,7  
**Weave:** Plain  
**Finish:** scoured

**suter-kunststoffe ag**  
**swiss-composite.ch**  
 CH-3312 Fraubrunnen 031 763 60 60 Fax 031 763 60 61

Construction:	Warp	Weft
Material:	Aramid	Aramid
Yield:	42 tex	42 tex

Technical Data		Unit	Target	+/-	Tolerance
Fibre density <sup>1) 3)</sup>	Warp	g/cm <sup>3</sup>	n.G.	+/-	n.G.
	Weft	g/cm <sup>3</sup>	n.G.	+/-	n.G.
Linear density <sup>1)</sup>	Warp	tex	42	+/-	2
	Weft	tex	42	+/-	2
Twist <sup>1)</sup>	Warp	T/m		+/-	
	Weft	T/m		+/-	
Setting	Warp	thr./cm	8,7	+/-	0,2
	Weft	thr./cm	8,7	+/-	0,2
Weight		g/m <sup>2</sup>	75	+/-	3
Dry Weight		g/m <sup>2</sup>	74	+/-	2
Moisture content		%	5,0		
Thickness <sup>2)</sup>		mm	0,16	+/-	0,04
Width		cm	as ordered	+/-	1

1) or n.G.: depending on order and yarn specification

2) approximate value, not for release

3) no measure, certified by supplier

**Remark:**

The values describe the properties of the fabric based on a limited production period.

<b>Date</b> 21.05.2015	<b>QM</b> Sybille Büscher	<b>This datasheet does not include revision service.</b>
---------------------------	------------------------------	--