

TECHNICAL DATASHEET



Article: Style 140
Setting [threads/cm]: 13,0/13,0
Weave: Twill 2/2
Finish: scoured

suter-kunststoffe ag
swiss-composite.ch
 CH-3312 Fraubrunnen 031 763 60 60 Fax 763 60 61

Construction:	Warp	Weft
Material:	Aramid	Aramid
Yield:	42 tex	42 tex

Technical Data		Unit	Target	+/-	Tolerance
Fibre density ^{1) 3)}	Warp	g/cm ³	1,45	+/-	0,05
	Weft	g/cm ³	1,45	+/-	0,05
Linear density ¹⁾	Warp	tex	42	+/-	2
	Weft	tex	42	+/-	2
Twist ¹⁾	Warp	T/m		+/-	
	Weft	T/m		+/-	
Setting	Warp	thr./cm	13,0	+/-	0,4
	Weft	thr./cm	13,0	+/-	0,4
Weight		g/m ²	110	+/-	4
Dry Weight		g/m ²	110	+/-	4
Moisture content		%	5,0		
Thickness ²⁾		mm	0,20	+/-	0,05
Width		cm	as ordered	+/-	1

1) or n.G.: depending on order and yarn specification

2) approximate value, not for release

3) no measure, certified by supplier

Remark:

The values describe the properties of the fabric based on a limited production period.

Date 14.08.2015	QM Sybille Büscher	This datasheet does not include revision service.
---------------------------	------------------------------	--