

TECHNICAL DATASHEET



Article: Style 354
Setting [threads/cm]: 8,0/6,0
Weave: Plain
Finish: loomstate / corona treatment

suter-kunststoffe ag
swiss-composite.ch
 CH-3312 Fraubrunnen 031 763 60 60 Fax 763 60 61

Construction:	Warp	Weft
Material:	UHMW-PE	UHMW-PE
Yield:	88 tex	88 tex

Technical Data		Unit	Target	+/-	Tolerance
Fibre density ¹⁾³⁾	Warp	g/cm ³	0,97	+/-	0,05
	Weft	g/cm ³	0,97	+/-	0,05
Linear density ¹⁾	Warp	tex	88	+/-	4
	Weft	tex	88	+/-	4
Twist ¹⁾	Warp	T/m		+/-	
	Weft	T/m		+/-	
Setting	Warp	Fd./10cm	8,0	+/-	0,4
	Weft	Fd./10cm	6,0	+/-	0,3
Weight		g/m ²	125	+/-	5
Dry Weight		g/m ²	125	+/-	5
Moisture content		%	0,5		
Thickness ²⁾		mm	0,37	+/-	0,04
Width		cm	as ordered	+/-	1

1) or n.G.: depending on order and yarn specification

2) approximate value, not for release

3) no measure, certified by supplier

Remark:

The values describe the properties of the fabric based on a limited production period.

Date 13.02.2014	QM Sybille Büscher	This datasheet does not include revision service.
---------------------------	------------------------------	--