


Grilonit® F 704

Polypropylene glycol diglycidyl ether



Characteristics

- low toxicity and vapour pressure
- polymeric difunctional glycidyl ether
- insoluble in water
- flexibilizer with reduced activity and limited diluting power

Product Specifications

Epoxy value	[eq/100g]	0.300 – 0.330
Colour Gardner		0 - 2
Total chlorine	[%]	max. 3.0
Hydrolysable chlorine	[%]	max. 0.1
Water	[%]	max. 0.2

Other typical Properties

Density at 20°C	[g/cm ³]	1.06
Flash point, (Abel-Pensky)	[°C]	> 100
Viscosity (Höppler) at 25°C	[mPa*s]	45
Solubility		insoluble in water

EMS-GRILTECH has the capability to produce many other glycidyl ethers and esters. Make use of our expertise.

Recommendations are given in good faith, but are not guaranteed. No liability can be accepted. This also applies to third-party patent rights.

01.05.2009

EMS-CHEMIE AG
Business Unit EMS-GRILTECH
Via Innovativa 1
CH-7013 Domat/Ems
Phone +41 81 632 7202, Fax +41 81 632 7407
www.emsgriltech.com

GRILONIT®
EMS